

RÄUCHERGOLD

Natural wood fibers

Basic raw material

Selected leaf wood

Chemical and physical properties

Colour		light brown
Structure		cubic
Average particle size / particle range		2.5 mm - 3.5 mm
Oxide ash (850 °C, 4 h)	~	1 %
pH-value (10 % suspension)		4.5 - 6.5
Bulk density (in accordance with DIN EN ISO 60)		250 g/L - 350 g/L

Screen analysis (with RETSCH vibrating sieve) with an interior mesh aperture of:

<u>> 5 mm</u>	<u>> 3.15 mm</u>	<u>> 2 mm</u>
max. 5 %	25 % - 70 %	min. 95 %

General remarks

RÄUCHERGOLD wood fibers are environment friendly products, gained from replenishable raw materials.

As with all natural products slight differences to the above given values may arise.

Release date: 2022-08 / 1 page